SUPREME GPPS SC206E General Purpose Polystyrene Supreme Petrochem Ltd. Web



Product Description				
This grade is for application	s like synthetic pencils a	and extrusion coa	ting.	
General				
Material Status	Commercial: Discontinued			
Search for UL Yellow Card	Supreme Petrochen	า Ltd.		
Availability	Africa & Middle Eas	t • Europe		
	 Asia Pacific 	North Am	erica	
Features	Food Contact	 High Clari 	ity	 High Flow
	Acceptable			
Uses	• Cups	 Medical/H 	lealthcare	 Packaging
		Applicatio	ns	ar a 133 print, 234 printerna primary rapor programa processo for the Control of St.
Agency Ratings	• FDA 21 CFR 177.16	340		
Forms	 Pellets 			
Processing Method	Extrusion Coating	 Injection I 	Molding	
Physical	No	ominal Value Un	nit	Test Method
Specific Gravity		1.05 g/c	cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°	12 g/1	10 min	ASTM D1238
C/5.0 kg)				,
Mechanical	No	ominal Value Un	nit	Test Method
Tensile Strength		44.1 MF	^D a	ASTM D638
Tensile Elongation (Break)		5.0 %		ASTM D638
Flexural Modulus		2750 MF	⊃a	ASTM D790
Flexural Strength	E DEL SANA E TERRETARIA ANTARA ANTARA MANTE DAN DEL CASA LAS ARESTES EN ESPECIALES.	58.8 MF	⊃a	ASTM D790
Impact	No	ominal Value Ur	1it	Test Method
Notched Izod Impact		20 J/r	n	ASTM D256
Thermal	No	ominal Value Ur	nit	Test Method
Deflection Temperature Und	der Load	83.0 °C		ASTM D648
(1.8 MPa, Unannealed)				
Vicat Softening Temperatur	е	101 °C		ASTM D1525



UL and the UL logo are trademarks of UL LLC ©
2013. All Rights Reserved. UL IDES
The information presented on this datasheet was
acquired by UL IDES from the producer of the
material. UL IDES makes substantial efforts to assure
the accuracy of this data. However, UL IDES
assumes no responsibility for the data values and
strongly encourages that upon final material
selection, data points are validated with the material
supplier.

Revision History

Added to Prospector: November, 1999 Last Updated: 11/12/2007

Find an Alternative to This Grade

Don't Have a Prospector account?

www.ides.com/alternatives

Register for free: www.ides.com/pse