

# LL6208AF

## Product Technical Information

LLDPE film products

## Applications

LL6208AF has been developed for use in rich blends in heavy duty sacks, liners and other thin film applications requiring excellent mechanical performance. This grade is also recommended for artificial grass applications

## Benefits and Features

LL6208AF is a linear low density polyethylene copolymer containing hexene-1 as the co-monomer. It offers the following properties:

- Excellent impact strength and puncture resistance
- High tear strength
- Good optical properties
- Good bubble stability
- Excellent sealability and hot-tack strength

If corona treatment is necessary, the level should normally be in the range 38-48 mN/m.

We recommend that you consult your INEOS O&P Europe technical representative for further advice on the use of LL6208AF.

Properties		Test Method	Value	Units
<b>Physical</b>				
Melt flow rate		ISO 1133 Condition 4	0.9 (2.16kg)	g/10 min
Density		ISO 1183 Method D	920	kg/m <sup>3</sup>
Vicat softening temperature		ISO 306 Method A	109	°C
Additives: antioxidants, CaSt				
<b>Film*</b>				
Dart drop impact		ASTM D1709 Method A	250	g
Tensile stress at yield	MD/TD	ISO 0527	12/12	MPa
Tensile stress at break	MD/TD	ISO 0527	60/44	MPa
Elongation at break	MD/TD	ISO 1184	750/900	%
1% Secant modulus		ISO 1184	180/240	MPa
Elmendorf tear strength	MD/TD	ASTM D1922	245/545	g/25 µm
Haze		ASTM D1003	10	%
Gloss (45°)		ASTM D2457	61	%

- Data should not be used for specification works

\* 38 µm film, 2:1 blow-up ratio, 225°C melt temperature - MD = machine direction TD = transverse direction

November, 2009

Published by

**INEOS** Olefins & Polymers Europe