

HIPTEN 22020

DESCRIPTION:

HIPTEN[®] 22020 is low density polyethylene resin developed for film extrusion. This grade has good mechanical and optical properties and good draw down characteristics. Film produced from this grade has good appearance and heat sealability, good moisture barrier and adhesion properties.

PROCESSING RECOMMENDATIONS:

Processing temperature: 180-200°C

Blow-up ratio: 2–3 : 1

PROPERTIES:

| PROPERTY | TEST METHOD | UNIT | VALUE |
|------------------------------|--|-------------------|------------------|
| MELT FLOW RATE | SRPS EN ISO 1133-1 2,16/190°C | g/10 min | 2,0 |
| DENSITY | SRPS EN ISO 1183-2 | kg/m ³ | 921 |
| TENSILE STRENGTH AT BREAK | SRPS EN ISO 527-3 SRPS EN ISO 527-2 | MPa | 20/19** 12 |
| TENSILE STRENGTH AT YIELD | SRPS EN ISO 527-3 SRPS EN ISO 527-2 | MPa | -/12** 9 |
| ELONGATION | SRPS EN ISO 527-3 SRPS EN ISO 527-2 | % | 650/750** 600 |
| VICAT SOFTENING POINT | SRPS EN ISO 306 | °C | 96 |
| HARDNESS | SRPS EN ISO 868 | Shore D | 46 |
| DART DROP F50 (METHOD A) | ASTM D 1709 | g | 120* |
| TEAR STRENGTH (ELMENDORF) | ASTM D 1922 | g /mil | 350/450** |

**Results obtained on film sample of 40 µm; blow-up ratio: 2,7 : 1

*Results obtained on film sample in MD/TD direction
(MD – machine direction; TD – transversal direction)

The values in this review are characteristic and are provided for guidance purposes only.

APPLICATION:

Production of laminated food-packaging materials.

HIPTEN[®] 22020 has Health Certificate issued by Institute for Health Protection of Serbia.

Z

E

T

P

I

H

STORAGE:

Polymer pellets are packed in LDPE bags, each bag weighs 25 kg. Bags are arranged on pallets and wrapped in stretch foil. One pallet has total polymer weight of 1250 kg.

Polyethylene is combustible material, therefore fire prevention measures in warehouses should be applied. Keep the polymer protected from harmful influences of heat, direct sunlight and high atmospheric humidity during storage.

If resin is stored under unfavourable conditions of large fluctuation in ambient temperature and atmospheric humidity, atmospheric moisture can condense inside the packaging. In such case, it is recommended to dry pellets before use.

The producer has no responsibility for any damage caused with the inappropriate storage.

REACH:

„HIP-Petrohemija“ a.d., Pancevo, Serbia, with applying the existing standards ISO 9001:2008, ISO 14001:2004 and OHSAS 18001: 2007, follows completely the highest standards by which there are regulated environmental protection, human health and safety protection and herewith it expresses its intention to meet all the requirements which are prescribed by REACH regulation.

Registration of all the substances of potential export interest has been made with European Agency for Chemicals in Helsinki, in accordance with the prescribed deadlines, therefore in this way it enables further undisturbed placement and sale of „HIP-Petrohemija“ a.d. products without any limits at EU Market.

As the only representative for „HIP-Petrohemija“ a.d. in EU, pursuant to Article 8 of REACH regulation, there has been designated **ReachLaw Ltd., Helsinki, Finland.**

RECYCLING:

Polyethylene is a material suitable for recycling.

The waste, that could appear during processing, should be kept clean before new usage through direct recycling.

CONTACT:

Sale:

T: +381 13 341 874

F: +381 13 347 173

E: polyolefins.sales@hip-petrohemija.rs

Technical information:

T: +381 13 307 103

F: +381 13 351 407

E: customer.support@hip-petrohemija.rs

Z

E

T

P

I

H